

## RESIDHERE® AM 145

GUM ROSIN MODIFIED WITH MALEIC ANHYDRIDE.

**RESIDHERE® AM 145** IS IDEAL FOR USE ON LACQUERS, SEALANTS, NITRO CELLULOSE-BASED VARNISHES AND SYNTHETIC ENAMELS. INCREASE ADHESION, PROMOTE HIGH GLOSS, HARDNESS AND FAST DRYING.

### PROPERTIES

Analysis	UN	Specification	Typical Values	Method
COLOR GARDNER	-	Max. 8	6.5	ML SCDV 006
ACID NUMBER	mg KOH/g	30- 40	34	ML SCDV 001
SOFTENING POINT	°C	140- 150	148	ML SCDV 002

### COMPATIBILITY

COMPATIBLE WITH ALIPHATIC AND AROMATIC SOLVENTS, ACETATES AND DRYING OILS. INSOLUBLE IN ALCOHOLS.

### PACKAGING

Type	Size	Shelf Life
KRAFT PAPER BAGS (FLAKES)	25 kg	12 months

### REGULATORY STATUS

FDA 175.105 / FDA 175.300 / EUROPEAN REGULATION (EU) NO. 10/2011.

### DISCLAIMER

To prevent accidents and environmental impacts, please check the product SDS.

We request our customers to test our products before using them on industrial scale. The user of our products bears the responsibility of determining their suitability for a particular application or formulation or determining that the products or their use does not infringe any intellectual property. We do not assume any responsibility or warranty, expressed or implied, resulting from handling, usage and storage whether performed according to the instructions contained in this document, whether used alone or in combination with other products. The buyer assumes all responsibility and liability for loss or damage arising from the handling and use of our products, either alone or in combination with other products.

